

### Specifications

|                     |  |
|---------------------|--|
| Collection(s)       | -  |
| Colour(s)           | Beige, Crimson, Custard, Denim, Latte, Mocha, Slate, Steel |
| Warwick Brand       | Halo   |
| Usage               | Drapery / Heavy Commercial                                 |
| Composition         | 100% Polyester   |
| Pattern match       | No   |
| Pattern repeat (cm) | Plain  |
| Railroaded          | No   |
| Continuous          | No   |
| Lead weighted       | No   |
| Width (cm)          | 137  |
| Weight (gsm)        | 301  |
| Origin              | AU   |
| Stain Repellent     | No   |
| FIAA Care Label*    | 8  |
| WCAA Care Label*    | 4  |

\*Please refer to Warwick Price List or Website [www.warwick.com.au](http://www.warwick.com.au)

### Test Results

|                                     |                      |
|-------------------------------------|----------------------|
| Abrasion                            |                      |
| Martindale (ISO 12947, 12kPa)       | 150,000 Cycles       |
| Seam slippage (mm)                  |                      |
| (ISO 13936-2, Load 180)             | Warp 3.00, Weft 2.80 |
| Pilling resistance                  |                      |
| (ISO 12945-2)                       | 4                    |
| Colourfastness to light             |                      |
| Xenon arc (ISO 105-B02, blue std 6) | >6                   |
| Colourfastness to rubbing           |                      |
| (ISO 105-X12)                       | Dry 4, Wet 3/4       |
| Dimension change - laundering (%)   |                      |
| (ISO 5077/ISO 6330. 7BA)            | Warp 0.00, Weft 0.00 |
| Dimension change - hanging (%)      |                      |
| (AS2663.1.B)                        | Warp 0.00, Weft 0.00 |
| Free and Hydrolysed formaldehyde    |                      |
| (ISO 14184-1:1998)                  | Not Detectable       |
| Flammability AS/NZS 1530.2-1993     |                      |
| Flamability Index (0 - 100)         | -                    |
| Spread Factor (0 - 40)              | Length -, Width -    |
| Heat Factor (0 - upward)            | Length -, Width -    |
| Flammability AS/NZS 1530.3-1999     |                      |
| Ignitability (0 - 20)               | 9                    |
| Spread of flame (0 - 10)            | 0                    |
| Heat evolved (0 - 10)               | 1                    |
| Smoke developed (0 - 10)            | 5                    |

