

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTa Product Testing
A.B.N 43 006 014 106


1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400

TEST REPORT

Client : Warwick Fabrics Aust Pty Ltd
6-10 Sackville Street
Collingwood VIC 3066

Test Number : 25-005074
Issue Date : 16/01/2026
Print Date : 16/01/2026

Sample Description	Clients Ref : "Edris"	Julia Hope
	Sheer woven fabric	
	Colour :	Grey
	End Use :	Curtains
	Nominal Composition : 100% Polyester	
	Nominal Mass per Unit Area/Density : 70g/m2	



368768

80858

Page 1 of 2

© Australian Wool Testing Authority Ltd
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing
Accreditation Numbers: 983, 985, and 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTa Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTa Product Testing and AWTa Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTa Ltd.


Chris Campbell
APPROVED SIGNATORY




MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTa Product Testing
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400

TEST REPORT

Client : Warwick Fabrics Aust Pty Ltd
6-10 Sackville Street
Collingwood VIC 3066

Test Number : 25-005074
Issue Date : 16/01/2026
Print Date : 16/01/2026

AS 1530.2-1993

Methods for Fire Tests on Building Materials, Components and Structures.

Part 2: Test for Flammability of Materials

Date Tested	16-01-2026		
Flammability Index	1		
	Length	Width	
Spread Factor	0	0	
Heat Factor	1	1	
Maximum height (d)			
Mean	1.1	1.1	
Coefficient of Variation	18.8	18.8	%
Heat (a)			
Mean	1.5	1.5	°C.min
Coefficient of Variation	0.0	0.0	%
Number of Specimens Tested	6	6	
Observation	Visible smoke, Melting		

Tested as received.

These test results relate only to the behaviour of the test specimens of the material under the particular conditions of the test, and they are not intended to be the sole criterion for assessing the potential fire hazard of the material in use.

368768

80858

Page 2 of 2

© Australian Wool Testing Authority Ltd
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing
Accreditation Numbers: 983, 985, and 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTa Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTa Product Testing and AWTa Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTa Ltd.

Chris Campbell
APPROVED SIGNATORY



MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR