

# DAVID J HEFFER AND ASSOCIATES

Consulting Textile  
Technologists

djheffer@djha.com.au  
www.djha.com.au

22 Hicks Street, Lara, Vic, 3212  
Tel: (03) 5282 1337  
Fax: (03) 5282 1003  
ABN. 87 710 470 062



## LABORATORY REPORT

Date : 28 October 2020

Report Number: 206085

Client: WARWICK FABRICS (AUST) PTY LTD  
PO BOX 1242  
COLLINGWOOD VIC 3066

Reference: Jessica Fitzgerald

Sample: woven, Peninsula, 100% polyester

Results:

Flammability (AS1530-1993 Part 2)

| Direction | Speed factor (S) | Heat factor (H) | Spread factor (E) | Flammability index |
|-----------|------------------|-----------------|-------------------|--------------------|
| warp      | -                | 2               | 11                | 16                 |
| weft      | -                | 2               | 14                |                    |

Note: The heat factor (H) will range from 0 upwards, the speed factor (S) from 0 to 60 and the spread factor (E) from 0 to 40. The value of the flammability index (I) will range from 0 to 100 for most materials.

DAVID J HEFFER  
DIRECTOR