

# AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing  
A.B.N 43 006 014 106  
1st Floor, 191 Racecourse Road, Flemington, Victoria 3031  
P.O Box 240, North Melbourne, Victoria 3051  
Phone (03) 9371 2400

## TEST REPORT

**Client :** Warwick Fabrics Aust Pty Ltd  
6-10 Sackville Street  
Collingwood VIC 3066

**Test Number :** 20-003343  
**Issue Date :** 14/07/2020  
**Print Date :** 14/07/2020

**Sample Description** Clients Ref : "Compass" Cara Hunt  
Coated woven fabric with blockout coating  
End Use : Drapery  
Nominal Composition : 100% Polyester  
Nominal Mass per Unit Area/Density : 310g/m<sup>2</sup>  
Nominal Thickness : 1mm

AS/NZS 1530.3-1999

### Methods for Fire Tests on Building Materials, Components and Structures Part 3: Simultaneous Determination of Ignitability, Flame Propagation, Heat Release and Smoke Release

Face tested:	Face		
Date tested:	14/07/2020		
	Standard Error	Mean	
Ignition time	0.55	5.33	min
Flame propagation time	Nil	Nil	sec
Heat release integral	11.2	76.8	kJ/m <sup>2</sup>
Smoke release, log d	0.0720	-0.3104	
Optical density, d		0.5181	/ metre
No of samples which ignited		5	
For Samples which ignited			
Smoke Release (Log D) - Mean		-0.3104	
Smoke Release (Log D) - Standard Error		0.0720	
No of samples which did not ignite		4	
For Samples which did not ignite			
Smoke Release (Log D) - Mean		-0.8442	
Smoke Release (Log D) - Standard Error		0.0802	
Number of specimens tested:		9	

208617

45179

Page 1 of 2

© Australian Wool Testing Authority Ltd  
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing  
- Chemical Testing : Accreditation No. 983  
- Mechanical Testing : Accreditation No. 985  
- Performance & Approvals Testing : Accreditation No. 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.

APPROVED SIGNATORY



MICHAEL A. JACKSON B.Sc. (Hons)  
MANAGING DIRECTOR

# AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing

A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031

P.O Box 240, North Melbourne, Victoria 3051

Phone (03) 9371 2400

## TEST REPORT

**Client :** Warwick Fabrics Aust Pty Ltd  
6-10 Sackville Street  
Collingwood VIC 3066

**Test Number :** 20-003343  
**Issue Date :** 14/07/2020  
**Print Date :** 14/07/2020

### Regulatory Indices:

Ignitability Index	15	Range 0-20
Spread of Flame Index	0	Range 0-10
Heat Evolved Index	3	Range 0-10
Smoke Developed Index	6	Range 0-10

The reaction of thin unsupported flexible materials to flame impingement can be assessed in accordance with AS 1530.2. Where materials of thickness less than 2mm that are sufficiently flexible to be bent by hand around a mandrel of 2mm diameter or less are subjected to the test described herein, they should also be subjected to the test in AS 1530.2.

Inconsistent flame spread behaviour was observed. Only 2 of the 9 specimens registered flame spread. The Spread of Flame Index quoted above is based on these 2 specimens.

Ignition is initiated by a pilot flame that is held near, but does not touch the specimen. A material that does not ignite during the standard test may ignite if contacted with a pilot flame during the test.

The specimens were mounted to simulate use in an unsupported or free hanging mode. The results may be significantly different when mounted to simulate a wall cladding or upholstery application.

To allow free movement of sample during testing all corners were folded away from the clamps.

Each test specimen was sandwiched between two layers of galvanised welded square mesh made from wire of nominal diameter 0.8mm and nominal spacing 12mm in both directions, stapled through at four points, each 100mm from the centre of the sample and the assembly clamped in four places.

These results only apply to the specimen mounted, as described in this report. The result of this fire test may be used to directly assess fire hazard, but it should be recognised that a single test method will not provide a full assessment of fire hazard under all fire conditions.

208617

45179

Page 2 of 2

© Australian Wool Testing Authority Ltd  
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing

- Chemical Testing  
- Mechanical Testing  
- Performance & Approvals Testing

: Accreditation No. 983  
: Accreditation No. 985  
: Accreditation No. 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.

0204/11/06

APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc. (Hons)  
MANAGING DIRECTOR

