

DAVID J HEFFER AND ASSOCIATES

Consulting Textile
Technologists

djheffer@djha.com.au
www.djha.com.au

22 Hicks Street, Lara, Vic, 3212
Tel: (03) 5282 1337
Fax: (03) 5282 1003
ABN. 87 710 470 062



LABORATORY REPORT

Date: 6 May 2015

Report Number: 150916

Client: WARWICK FABRICS (AUST) PTY LTD
PO BOX 1242
COLLINGWOOD VIC 3066

Reference: Shana Parkinson

Sample: woven, Fitzgerald, 100% polyester

Results:

Flammability (AS1530-1993 Part 2)

Sample	Direction	Speed factor (S)	Heat factor (H)	Spread factor (E)	Flammability index
1	warp	-	4	32	36
	weft	-	3	22	

Note: The heat factor (H) will range from 0 upwards, the speed factor (S) from 0 to 60 and the spread factor (E) from 0 to 40. The value of the flammability index (I) will range from 0 to 100 for most materials.

DAVID J HEFFER
DIRECTOR