

NZWTA

No. 1162443.4

(Please quote this number in all correspondence)

CLIENT:

SAMPLE RECEIVED FROM:

Date: 5.12.16

Warwick Fabrics Ltd. PO Box 100-721

Warwick Fabrics Ltd.

NSMC, Auckland

SAMPLE DESCRIPTION:

Woven fabric - Jali, 100% Polyester, 126gsm, linen

Attn.: Ana Horomia-Blair

colour.

Client Order No.:

Client Reference:

1 of 1

AS 1530.2-1993 – METHODS FOR FIRE TESTS ON BUILDING MATERIALS, COMPONENTS AND STRUCTURES PART 2: TEST FOR FLAMMABILITY OF MATERIALS

This test was carried out by a NATA accredited subcontracted laboratory

When face and back are tested, the worst results are quoted.

	Length	Width
Maximum Height (D) – Mean	2.0	2.0
CV%	0.0	0.0
Time (t) – Mean	N/A	N/A
CV%	N/A	N/A
Heat (A) - Mean (°C.min.)	1.5	1.5
CV%	0.0	0.0
Number of Test Specimens	6	6
Observation	Visible smoke & melting	

	Length	Width
Speed Factor (S)	N/A	N/A
Spread Factor (E)	0	0
Heat Factor (H)	1	1

Flammability Index calculation: I = H + E or I = H + S

Flammability Index = 1

These test results relate only to the behaviour of the test specimens of the material under the particular conditions of the test, and they are not intended to be the sole criterion for assessing the potential fire hazard of the material in use.

"THIS REPORT APPLIES ONLY TO THE SAMPLES TESTED"

Except where the sample is drawn independently by NZWTA Ltd. NZWTA Ltd makes no warranty, implied or otherwise as to the source of the tested sample. The above test results are not certified due to the adoption of modified and/or non-standard procedures designed to provide THE CLIENT WITH GUIDANCE INFORMATION ONLY. Except where precluded by law, no responsibility can be accepted by NZWTA Ltd for any claim which may arise from any person acting on information contained herein.

L A Greer Signatory C Judan Signatory 16/12/2016

New Zealand Wool Testing Authority Ltd Cnr Bridge & Lever Streets, PO Box 12065

Ahuriri, Napier 4144, New Zealand

T+64 6 835 1086, F+64 6 835 6473 Email: testing@nzwta.co.nz