

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing

A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031

P.O Box 240, North Melbourne, Victoria 3051

Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

Client : Warwick Fabrics Aust Pty Ltd
6-10 Sackville Street
Collingwood VIC 3066

Test Number : 19-002480
Issue Date : 30/05/2019
Print Date : 30/05/2019

Sample Description Clients Ref : "Lorne"
Woven Fabric
Colour : Beige
End Use : Upholstery
Nominal Composition : 100% Polyester
Nominal Mass per Unit Area/Density : 481g/m2

AS/NZS 1530.3-1999

Methods for Fire Tests on Building Materials, Components and Structures Part 3: Simultaneous Determination of Ignitability, Flame Propagation, Heat Release and Smoke Release

Face tested:	Face		
Date tested:	29/05/2019		
	Standard Error	Mean	
Ignition time	0.09	10.40	min
Flame propagation time	Nil	Nil	sec
Heat release integral	2.8	70.2	kJ/m ²
Smoke release, log d	0.0130	-0.7309	
Optical density, d		0.1863	/ metre
Number of specimens ignited:		6	
Number of specimens tested:		6	
Regulatory Indices:			
Ignitability Index		10	Range 0-20
Spread of Flame Index		0	Range 0-10
Heat Evolved Index		2	Range 0-10
Smoke Developed Index		5	Range 0-10

167351

35941

Page 1 of 2

© Australian Wool testing Authority Ltd
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing

- Chemical Testing
- Mechanical Testing
- Performance & Approvals Testing

: Accreditation No. 983
: Accreditation No. 985
: Accreditation No. 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc. (Hons)
MANAGING DIRECTOR

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing

A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031

P.O Box 240, North Melbourne, Victoria 3051

Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

Client : Warwick Fabrics Aust Pty Ltd
6-10 Sackville Street
Collingwood VIC 3066

Test Number : 19-002480
Issue Date : 30/05/2019
Print Date : 30/05/2019

These results only apply to the specimen mounted, as described in this report. The result of this fire test may be used to directly assess fire hazard, but it should be recognised that a single test method will not provide a full assessment of fire hazard under all fire conditions.

The reaction of thin unsupported flexible materials to flame impingement can be assessed in accordance with AS 1530.2. Where materials of thickness less than 2mm that are sufficiently flexible to be bent by hand around a mandrel of 2mm diameter or less are subjected to the test described herein, they should also be subjected to the test in AS 1530.2.

Specimens tended to flash before ignition. Ignition was based on the occurrence of a single flash of flame which lasted longer than 10 seconds.

The specimens melted away from the area of maximum heat and produced flaming droplets during the test. Due to this phenomena it should be recognised that this test result may not be a true indication of the product's fire hazard properties.

The specimens melted and flowed away from the area of maximum heat during the test. Due to this phenomena it should be recognised that this test result may not be a true indication of the product's fire hazard properties.

To allow free movement of sample during testing all corners were folded away from the clamps.

Each test specimen was sandwiched between two layers of galvanised welded square mesh made from wire of nominal diameter 0.8mm and nominal spacing 12mm in both directions, stapled through at four points, each 100mm from the centre of the sample and the assembly clamped in four places.

167351

35941

Page 2 of 2

© Australian Wool testing Authority Ltd
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing

- Chemical Testing
- Mechanical Testing
- Performance & Approvals Testing

: Accreditation No. 983
: Accreditation No. 985
: Accreditation No. 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc. (Hons)
MANAGING DIRECTOR