


DAVID J HEFFER AND ASSOCIATES

Consulting Textile
Technologists

22 Hicks Street, Lara, Vic, 3212
Tel: (03) 5282 1337

djheffer@djha.com.au
www.djha.com.au

ABN. 87 710 470 062



LABORATORY REPORT

Date : 25 January 2023

Report Number: 237638

Client: WARWICK FABRICS (AUST) PTY LTD
PO BOX 1242
COLLINGWOOD VIC 3066

Reference: Jessica Fitzgerald

Sample: woven, (Apollo, Marengo, Shelly), 100% polyester, colour: alabaster

Results:

Flammability (AS1530-1993 Part 2)

Direction	Speed factor (S)	Heat factor (H)	Spread factor (E)	Flammability index
warp	-	1	1	2
weft	-	1	1	

Note: The heat factor (H) will range from 0 upwards, the speed factor (S) from 0 to 60 and the spread factor (E) from 0 to 40. The value of the flammability index (I) will range from 0 to 100 for most materials.

DAVID J HEFFER
DIRECTOR