

# DAVID J HEFFER AND ASSOCIATES

Consulting Textile  
Technologists

djheffer@djha.com.au  
www.djha.com.au

22 Hicks Street, Lara, Vic, 3212  
Tel: (03) 5282 1337  
Fax: (03) 5282 1003  
ABN. 87 710 470 062



## LABORATORY REPORT

Date: 23 February 2017

Report Number: 172717

Client: WARWICK FABRICS LTD  
12 APOLLO DRIVE  
MAIRANGI BAY, AUCKLAND  
NEW ZEALAND

Reference: Ana Horomia-Blair

Sample: woven, Leigh, Claudette, Theron, Zeta, 100% polyester

Results:

Flammability (AS1530-1993 Part 2)

Direction	Speed factor (S)	Heat factor (H)	Spread factor (E)	Flammability index
warp	-	1	2	2
weft	-	0	2	

Note: The heat factor (H) will range from 0 upwards, the speed factor (S) from 0 to 60 and the spread factor (E) from 0 to 40. The value of the flammability index (I) will range from 0 to 100 for most materials.

DAVID J HEFFER  
DIRECTOR