

ALPINE

Specifications

Collection(s)	Coordinate Library 3
Colour(s)	Ebony, Forest, Lemon, Natural, Sky, Steel
Warwick Brand	-
Usage	Drapery / Heavy Dom / Gen Comm
Composition	61% Polyester 27% Viscose 12% Linen
Pattern match	Yes
Pattern repeat (cm)	H: 9 x V: 9
Railroaded	No
Continuous	No
Lead weighted	No
Width (cm)	140
Weight (gsm)	370
Origin	AU
Stain Repellent	No
FIAA Care Label*	3
WCAA Care Label*	2

*Please refer to Warwick Price List or Website www.warwick.com.au

Test Results

Abrasion Martindale (ISO 12947, 12kPa)	20000-40000 Cycles
Seam slippage (mm) (ISO 13936-2, Load 180)	Warp 5, Weft 5
Pilling resistance (ISO 12945-2)	3/4
Colourfastness to light Xenon arc (ISO 105-B02, blue std 6)	5/6
Colourfastness to rubbing (ISO 105-X12)	Dry 4, Wet 4/5
Dimension change - laundering (%) (ISO 5077/ISO 6330. 7BA)	Warp -5.1, Weft -4.1
Dimension change - hanging (%) (AS2663.1.B)	Warp 0.1, Weft 0.1
Free and Hydrolysed formaldehyde (ISO 14184-1:1998)	Not Detectable
Flammability AS/NZS 1530.2-1993 Flamability Index (0 - 100)	-
Spread Factor (0 - 40)	Length -, Width -
Heat Factor (0 - upward)	Length -, Width -
Flammability AS/NZS 1530.3-1999 Ignitability (0 - 20)	-
Spread of flame (0 - 10)	-
Heat evolved (0 - 10)	-
Smoke developed (0 - 10)	-



COMMERCIAL TEXTILE ASSOCIATION
OF AUSTRALIA & NEW ZEALAND
LIMITED



GENERAL COMMERCIAL USE



Tested for harmful substances
according to Oeko-Tex Standard 100
HKC 23567 TESTEX
005339.0 CENTROCOT

