

ARIES

Specifications

Collection(s)	Tritan Plains 3, Tritan Plains 3 Stacker Book
Colour(s)	Bark, Charcoal, Granite, Marble, Pebble, Sand, Stone, Woodland
Warwick Brand	Halo, Tritan
Usage	Heavy Commercial
Composition	70% Polyester 30% Acrylic
Pattern match	No
Pattern repeat (cm)	Plain
Railroaded	Plain**
Width (cm)	145
Weight (gsm)	640
Origin	Non EU
Stain Repellent	Fluro Chem
FIAA Care Label*	11

*Please refer to Warwick Price List or Website www.warwick.com.au

**Fabrics marked Railroaded 'Plain' can be cut in either direction at the discretion of the manufacturer, and in consultation with the customer's preference. Fabric is sampled in the direction it comes up the roll (Non Railroaded).

Test Results

Abrasion Martindale (ISO 12947, 12kPa)	102,000 Cycles
Seam slippage (mm) (ISO 13936-2, Load 180)	Warp 5, Weft 4
Pilling resistance (ISO 12945-2)	5
Colourfastness to light Xenon arc (ISO 105-B02, blue std 6)	>6
Colourfastness to rubbing (ISO 105-X12)	Dry 4, Wet 4
Free and Hydrolysed formaldehyde (ISO 14184-1:1998)	Not Detectable
Flammability AS/NZS 1530.3-1999	
Ignitability (0 - 20)	10
Spread of flame (0 - 10)	0
Heat evolved (0 - 10)	2
Smoke developed (0 - 10)	7

