

Specifications

| | |
|---------------------|--|
| Collection(s) | Chambray Plain Hanger With, The White Hanger |
| Colour(s) | Ash, Charcoal, Clay, Denim, Duckegg, Dusk, Dusty Blue, Ecru, Elephant, Eucalyptus, Feather, Flint, Graphite, Ink, Ivory, Lake, Maize, Mandarin, Menthol, Mist, Mocha, Mushroom, Mustard, Nectar, Oatmeal, Onyx, Opal, Oyster, Pine, Raspberry, Rosewater, Seaglass, Silver, Snow, Steel, Stone, Storm, Tussock, Twine, Vanilla, Vapour, Zinc |
| Warwick Brand | - |
| Usage | Drapery / Heavy Commercial |
| Composition | 50% Cotton 50% Polyester |
| Pattern match | No |
| Pattern repeat (cm) | Plain |
| Railroaded | Plain** |
| Continuous | No |
| Lead weighted | No |
| Width (cm) | 138 |
| Weight (gsm) | 345 |
| Origin | Non EU |
| Stain Repellent | No |
| FIAA Care Label* | FW |
| WCAA Care Label* | 4 |

*Please refer to Warwick Price List or Website www.warwick.com.au

**Fabrics marked Railroaded 'Plain' can be cut in either direction at the discretion of the manufacturer, and in consultation with the customer's preference. Fabric is sampled in the direction it comes up the roll (Non Railroaded).

Test Results

| | |
|--|----------------------|
| Abrasion Martindale (ISO 12947, 12kPa) | 69,000 Cycles |
| Seam slippage (mm) (ISO 13936-2, Load 180) | Warp 3, Weft 3 |
| Pilling resistance (ISO 12945-2) | 4 |
| Colourfastness to light Xenon arc (ISO 105-B02, blue std 6) | >6 |
| Colourfastness to rubbing (ISO 105-X12) | Dry 5, Wet 4/5 |
| Dimension change - laundering (%) (ISO 5077/ISO 6330. 7BA) | Warp -2.3, Weft -1.0 |
| Dimension change - hanging (%) (AS2663.1.B) | Warp 0.0, Weft 0.0 |
| Free and Hydrolysed formaldehyde (ISO 14184-1:1998) | Not Detectable |
| Flammability AS/NZS 1530.2-1993 Flamability Index (0 - 100) | - |
| Spread Factor (0 - 40) | Length -, Width - |
| Heat Factor (0 - upward) | Length -, Width - |
| Flammability AS/NZS 1530.3-1999 Ignitability (0 - 20) | - |
| Spread of flame (0 - 10) | - |
| Heat evolved (0 - 10) | - |
| Smoke developed (0 - 10) | - |

