

KONA

Specifications

Collection(s)	Lomani Outdoor
Colour(s)	Ash, Calippo, Cloud, Hibiscus, Lagoon, Lime, Marine, Navy, Ocean, Pebble^, Pumice, Sand, Shell, Stone^, Sunshine, Tan, Turquoise
Warwick Brand	Halo, Sundec
Usage	Drapery / Heavy Dom / Gen Comm
Composition	100% Olefin
Pattern match	No
Pattern repeat (cm)	Plain
Railroaded	Plain**
Continuous	No
Lead weighted	No
Width (cm)	140
Weight (gsm)	277
Origin	Non EU
Stain Repellent	Fluro Chem
FIAA Care Label*	S
WCAA Care Label*	7

*Please refer to Warwick Price List or Website www.warwick.com.au

**Fabrics marked Railroaded 'Plain' can be cut in either direction at the discretion of the manufacturer, and in consultation with the customer's preference. Fabric is sampled in the direction it comes up the roll (Non Railroaded).

Test Results

Abrasion Martindale (ISO 12947, 12kPa)	20000-40000 Cycles
Seam slippage (mm) (ISO 13936-2, Load 180)	Warp 2.60, Weft 2.80
Pilling resistance (ISO 12945-2)	5
Colourfastness to light Xenon arc (ISO 105-B02, blue std 6)	>7
Colourfastness to rubbing (ISO 105-X12)	Dry 5, Wet 5
Dimension change - laundering (%) (ISO 5077/ISO 6330. 7BA)	Warp -0.30, Weft -0.10
Dimension change - hanging (%) (AS2663.1.B)	Warp 0.0, Weft 0.0
Free and Hydrolysed formaldehyde (ISO 14184-1:1998)	Not Detectable
Flammability AS/NZS 1530.2-1993 Flamability Index (0 - 100)	-
Spread Factor (0 - 40)	Length -, Width -
Heat Factor (0 - upward)	Length -, Width -
Flammability AS/NZS 1530.3-1999 Ignitability (0 - 20)	13
Spread of flame (0 - 10)	0
Heat evolved (0 - 10)	2
Smoke developed (0 - 10)	2

